

RAVEMUL P20

E03WD003 - 01/14

P 1 - 1

Ravemul P20 is a plasticized polyvinyl acetate aqueous dispersion with 48% solids and high viscosity.

	Unit	Value	Method
1. SUPPLY SPECIFICATIONS			
Solid content	%	48±2	MVPF 01
Brookfield viscosity	(1) mPa.s	40000±10000	UNI EN ISO 2555
pH		4.5±0.5	ISO 976
2. TYPICAL VALUES			
Minimum film-forming temperature	°C	0	UNI 8490-14
Average particles size	µm	0.4÷4.0	MVANS 20
Dispersing system		Polyvinyl alcohol	
Density at 23°C	kg/dm ³	1.1	MVPF 18
Mechanical stability		Excellent	MVAT 013
Plasticizer content	p.h.r.	18	

(1) RVT 20 rpm, spindle 7, 23 °C

APPLICATIONS

Paper, leather and textiles adhesives. Building adhesives and plasters.
Ravemul P20 is particularly suitable to prepare adhesives to use on automatic machines for the production of boxes and cases.

PACKAGING

Ravemul P20 is available in bulk and in 125 kg or 50 kg drums.

STORAGE

Ravemul P20 is stable for at least 6 months when stored between +5 and + 40°C.

Data, information and suggestions are provided for guidance purpose only. VINAVIL EGYPT for Chemicals S.A.E. accepts no responsibility for the results obtained therefrom, nor for their utilization in infringement of possible patent rights. The analytical methods are available on request.