

# VINAVIL P23

E03WD005 - 01/14

P 1 - 1

Vinavil P23 is a plasticized polyvinyl acetate aqueous dispersion with 42% solid content.

	Unit	Value	Method
<b>1. SUPPLY SPECIFICATIONS</b>			
Solid content	%	42±2	MVPF 01
Brookfield viscosity	(1) mPa.s	40000±10000	UNI EN ISO 2555
pH		4.5±0.5	ISO 976
<b>2. TYPICAL VALUES</b>			
Minimum film-forming temperature	°C	4	UNI 8490-14
Dispersing system		Polyvinyl alcohol	
Density at 23°C	kg/dm <sup>3</sup>	1.1	MVPF 18
Mechanical stability		Excellent	MVAT 013
Plasticizer content	p.h.r.	8	

(1) RVT 20 rpm, spindle 7, 23 °C

## APPLICATIONS

Building industries - wood adhesives - textile industry.

## PACKAGING

Vinavil P23 is available in bulk and in 125 kg or 50 kg drums.

## STORAGE

Vinavil P23 is stable for at least 6 months when stored between +5 °C and + 40°C.

Data, information and suggestions are provided for guidance purpose only. VINAVIL EGYPT for Chemicals S.A.E. accepts no responsibility for the results obtained therefrom, nor for their utilization in infringement of possible patent rights. The analytical methods are available on request.